





Serif™

Designed to promote creativity and facilitate teamwork, Serif is a slim CeramicSteel panel mounted with standoff mounts in a satin chrome finish. Precision cut edges are sealed with a durable lacquer, while rounded corners provide a modern, premium look.

Dimensions	Thickness	Weight	Depth	Depth From Wall to Face
1185 mm x 1185 mm / 47 in x 47 in	6,5 mm / 0.25 in	14,5 kg / 32 lbs	6,5 mm / 0.25 in	19 mm / 0.75 in
1185 mm x 1830 mm / 47 in x 72 in	6,5 mm / 0.25 in	22,5 kg / 50 lbs	6,5 mm / 0.25 in	19 mm / 0.75 in
1185 mm x 2420 mm / 47 in x 95 in	6,5 mm / 0.25 in	30 kg / 66 lbs	6,5 mm / 0.25 in	19 mm / 0.75 in

Color	Finish	Steelcase Finish Code	Approximate RAL Color	Approximate Pantone® Color
Alpine White 9912 XS 	Gloss	7680	9003	11-4601 TPG Bit of Blue
Surface Imaging 	Gloss	7699*	-	-

*7699 finish code only applicable to APAC COM orders in Steelcase Hedberg ordering system

Panel Property	Testing Standard	Unit	Value
Panel Thickness	EN 438-2:5	-	6,5 mm / 0.25 in
Length Tolerance	EN 438-2:6	mm	± 1
Width Tolerance	EN 438-2:6	mm	± 1
Squareness	Difference in diagonals of panels	mm	± 1.5
Fire Resistance	ASTM E84-16	-	Class A, 15/15
Corners	-	mm	Rounded, 4mm
Hole diameter	-	mm	10,5
Hole diameter tolerance	-	mm	+/- 0,5
Sharp edges enameled steel topside	UL1439	-	Smooth and round edges, to not cause a cut - type injury
Sharp edges enameled steel bottomside	UL1439	-	Smooth and round edges, to not cause a cut - type injury
Enamel Edge Chip Off	-	mm	Max. 0.5
Flatness	-	-	0,15%
Weight (typical)	-	kg/m ²	10,5

Element	Material
Face	a ³ CeramicSteel writing surface
Core	MDF 6 mm
Back	Galvanized steel

Surface Property	Testing Standard	Unit	Value
Gloss – Marker Surface	ISO 2813 / ASTM D523 20°	GU	85 -5 + 10 GU (80-95)
Color Tolerance	ISO 7724 / ASTM D2244-02	E ⁹⁴	≤ 1.5 (compared to reference sample)
Orange Peel	ISO 2813 / ASTM D523	mm	Short Wave ≤ 55 Long Wave ≤ 25 Distinctness of Image ≥ 60
Mohs Hardness	EN 15771	-	Min. 5
Scratch Resistance	ISO 15695	N	Min. 7
Pencil Hardness	ASTM D-3363	-	> 9H
Wear Resistance	ASTM C501	g	Max. 0.1 (abrasive S33 1 kg/1000 rev)
Impact	ISO 4532	-	No damage over 2 mm after 24h (20N load)
Coating Adhesion	EN 10209 Annex D	-	Min. Class 3
Total Thickness Enamel Top Coatings	ISO2178/ASTM B499	µm	85-120
Steel Thickness	-	mm	0.35 ± 0.03
Thickness Backside Enamel Coating	ISO2178/ASTM B499	µm	25-50
Acid Resistance	ISO 28706-1-9	-	Min. A
Chemical Resistance	ISO 28706-1-11	-	Min. A
Dry Erasability	PV 41.803	E94	≤ 1.5
Writability and Erasability	EN ISO 28762 §8.2	E94	≤ 0.5
Graffiti Resistance	EN ISO 28762 §9	-	No color or gloss change after cleaning



©2020 PolyVision Corporation. All rights reserved. Trademarks used herein are the trademarks of PolyVision Corporation or their respective owner. PolyVision Corporation reserves the right to make changes in product design, construction or detail, and to discontinue any product or material without notice.

*Pantone is a trademark of Pantone LLC. Use of the Pantone trademark does not imply an endorsement, sponsorship, or affiliation.