

Coil 3



CeramicSteel Surface (P 0.35)

0.35 mm thick steel coated with vitreous enamel surface with a total thickness of 0.49 mm

CeramicSteel Surface	Testing Standard	Unit	Value
Gloss – Type G	ISO 2813 ASTM D 523	Gloss units (GU)	65 ± 10 GU (20°)
Gloss – Type M	ISO 2813 ASTM D 523	Gloss units (GU)	60 ± 10 GU (60°)
Color tolerance	ISO 7724 ASTM D 2244-02	ΔE^{94}	$\Delta E^{94} \leq 1.5$ (compared to reference sample)
Reflectance	ISO 7724 ASTM D 2244-02	%	Y-Value up to 85%, depending on color
Defect appearance	EN 438-2:4		Free from defects liable to change the general appearance of the panel
Mohs hardness	EN 15771		Min. 5
Scratch resistance	ISO 15695	N	Min. 7
Pencil hardness	ASTM D-3363		> 9H
Wear resistance	ASTM C501	g	Max. 0.1 (abrasive S33 1 kg/1000 rev)
Impact	ISO 4532		No damage over 2 mm after 24 h (20 N load)
Coating adhesion	EN 10209 Annex D		Min. class 2
Porosity	EN ISO 2746	$\#/m^2$	< 10
Cold acid resistance	ISO 28706-1-9		Min. class A
Boiling acid resistance	ISO 28706-2-10	g/m^2	Max. 18.5
UV resistance	ISO 4892-3 (cycle 2)	ΔE^{94}	$\Delta E^{94} \leq 0.5$ (2000 h)
Color stability	ASTM C 538	ΔE^{94}	$\Delta E^{94} \leq 5$ (24 h)
Graffiti resistance	EN ISO 28722 (§7)		No color or gloss change after cleaning
Weight	N/A	kg/m^2	3.1

This CeramicSteel conforms to the following internationally recognized standards:

ISO 28722, Vitreous and porcelain enamels – Characteristics of enamel coatings applied to steel panels intended for architecture

European Normalization, EN 14431 – Vitreous and porcelain enamels – Characteristics of the enamel coatings applied to steel panels intended for architecture

Porcelain Enamel Institute, PEI 1001 – Specifications for architectural porcelain enamel

European Enamel Authority, EEA 7.13, 7.14 – Quality requirement for architectural panels