


Accord™

Discover the convenience of Accord — a frameless, mixed-media collaborative board combining the durable dry erase surface of CeramicSteel with a sound-absorbing tackboard. Offering a wide selection of sizes and material combinations, there is no longer a need to choose which surface suits your space best.

Dimensions


Horizontal Panel

Dimensions (W x H)	CeramicSteel Panel Dimensions (W)	Left OR Right / Double	Weight	Legend
1780 mm x 1185 mm 70" x 47"	1185 mm 47"	Left OR Right	21.8kg / 48.1 lbs	1
2425 mm x 1185 mm 94" x 47"	1830 mm 72"	Left OR Right	32.5kg / 71.1 lbs	2
3015 mm x 1185 mm 119" x 47"	2420 mm 95"	Left OR Right	42.2kg / 93 lbs	3
2420 mm x 1185 mm 95" x 47"	1185 mm 47"	Double	23.9kg / 52.7 lbs	4
3020 mm x 1185 mm 119" x 47"	1830 mm 72"	Double	34.6kg / 76.3 lbs	5
3610 mm x 1185 mm 142" x 47"	2420 mm 95"	Double	44.3kg / 97.7 lbs	6



Vertical Panel

Dimensions (W x H)	CeramicSteel Panel Dimensions (W)	Left OR Right / Double	Weight	Legend
1780 mm x 1830 mm 70" x 72"	1185 mm 47"	Left OR Right	33.7kg / 74.3 lbs	7
1780 mm x 2420 mm 70" x 95"	1185 mm 47"	Left OR Right	44.4kg / 97.9 lbs	8
2375 mm x 1830 mm 94" x 72"	1185 mm 47"	Double	37kg / 81.6 lbs	9
2375 mm x 2420 mm 94" x 95"	1185 mm 47"	Double	48.7kg / 107.4 lbs	10




Material

Element Whiteboards	Materials
Face	CeramicSteel writing surface
Core	MDF 12mm
Back	Aluminium 0.4mm
Element Sound-absorbing Material	Materials
Face	100% Solution Dyed (Color Through) Polyester
Element Vertical Bumper	Materials
Vertical Bumper	Black ABS, depth bumper to face = 4 mm

Color Options Whiteboards

Color		Finish	Approximate RAL Color	Approximate Pantone® Color
Arctic White 7671		Gloss	9003	11-4800 TPG Blanc de Blanc
White High Gloss 7655		Gloss	9003	Cool Gray 1C

Sound-absorbing Panel Color Options

Color		Finish	Approximate RAL Color	Approximate Pantone® Color
Stone		Felt	7030	Cool Gray 6
Dusk		Felt	7037	Warm Gray 7
Storm		Felt	7001	5425
Aqua		Felt	6004	5473
Space		Felt	5001	296
Arbor		Printed Felt	-	-

Surface Properties Whiteboard

Surface Property	Testing Standard	Unit	Value
Gloss - Marker Surface	ISO 2813 / ASTM D523 20°	GU	50-85
Gloss - Chalk Surface	ISO 2813 / ASTM D523 60°	GU	3.5-9.5
Color Tolerance	ISO 7724 / ASTM D2244-02	E ⁹⁴	≤ 1.5 (compared to reference sample)
Mohs Hardness	EN 15771	-	Min. 5
Scratch Resistance	ISO 15695	N	Min. 7
Pencil Hardness	ASTM D-3363	-	I 9H
Wear Resistance	ASTM C501	g	Max. 01 (abrasive S33 1 kg/1000 rev)
Impact	ISO 4532	-	No damage over 2mm after 24h (20N load)
Coating Adhesion	EN 10209 Annex D	-	Min. Class 3
Total Thickness Enamel Top Coatings	ISO2178/ASTM 8499	µm	85-120
Steel Thickness	-	mm	0.35 ± 0.03
Thickness Backside Enamel Coating	ISO2178/ASTM B499	µm	25-50
Acid Resistance	ISO 28706-1-9	-	Min. A
Chemical Resistance	ISO 28706-1-11	-	Min. A
Dry Erasability	PV 41.803	E ⁹⁴	≤ 1.5
Writability and Erasability	EN ISO 28762 §8.2	E ⁹⁴	≤ 0.5
Depth From Wall to Face	-	-	25 mm / 0.98"
Depth Bumper to Face	-	-	4 mm / 0.15"
Thickness	-	-	13 mm / 0.51"

Panel Properties Whiteboard

Panel Property	Testing Standard	Unit	Value
Panel Thickness	EN 438-2:5	mm	13
Length Tolerance	EN 438-2:6	mm	± 1
Width Tolerance	EN 438-2:6	mm	± 1
Squareness	Difference in diagonals of panels	mm	Max.1
Fire Resistance	ASTM E84-16	-	Class A, 15/15
Pencil Hardness	EN 14434 §6	-	Smooth and round edges, no risk of injury
Wear Resistance	EN 14434 §6	-	No risk of pinching/ squeezing
General Safety Requirements	EN 14434 §6	-	No small detachable parts
Sharp edges enameled steel topside	UL1439	-	Smooth and round edges, to not cause a cut - type injury
Sharp edges enameled steel bottomside	EL1439	-	Smooth and round edges, to not cause a cut - type injury
Enamel Edge Chip Off	-	mm	Max. 0.5
Flatness	-	-	0,15%
Weight (typical)	-	kg/m ²	13,0
Rounded edges	-	-	R 45
Edge Treatment	-	-	High Build, high solids siloxane coating

Sound-absorbing Panel Properties

Panel Property	Testing Standard	Unit	Value
Length Tolerance	EN 438-2:6	mm	± 1
Width Tolerance	EN 438-2:6	mm	± 1
Squareness	Difference in diagonals of panels	mm	Max.1
General Safety Requirements	EN 14434 §6	-	Smooth and round edges, no risk of injury
General Safety Requirements	EN 14434 §6	-	Smooth and round edges, no pinching/squeezing
General Safety Requirements	EN 14434 §6	-	Smooth and round edges, no small detachable parts
Fire Resistance	EN13501 ASTM E84	- -	B-s2, d0 Class A
Color Fastness to Artificial Light	AATCC 16.3		4.5 at 20AFU
Chemical resistance (Deminerlized water, Ethanol, Acetone, Carpet Stain remover)	EN 438-2	-	No Visible change
Stain resistance (Soda, Coffee, Soap)	EN 438-2	-	No Visible change
Stain resistance (Whiteboard marker, Permanent marker)	EN 438-2	-	Marker change of color
Sound-absorption (Noise reduction Coefficient)	-	-	NRC 0.45 - 0.80
Pinnable	-	-	Yes, not self-healing
Rounded edges			R 45

©2025 Polyvision Corporation. All rights reserved. Trademarks used herein are the trademarks of Polyvision Corporation or their respective owner. Polyvision Corporation reserves the right to make changes in product design, construction or detail, and to discontinue any product or material without notice.

*Pantone is a trademark of Pantone LLC. Use of the Pantone trademark does not imply an endorsement, sponsorship, or affiliation.

